



**SHIJIAZHANG CHENSHI IMPORT AND EXPORT CO.,LTD.**  
NO.168 TIANSHAN STREET, GAOXIN DISTRICT, SHIJIAZHANG CITY, HEBEI,  
CHINA

Tell: 0086 311 89871056      Fax : 0086 311 85831105  
Cell/whatsapp:+8618132602523      [www.chenshi-chem.com](http://www.chenshi-chem.com)

## TDS of Barium Sulphate Precipitated

### Technical Data Sheet

Density g/cm <sup>3</sup>	4.3-4.5	
Oil absorption g /100g	14-18	
BaSO <sub>4</sub> %	98.5min	
Fe <sub>2</sub> O <sub>3</sub> %	0.004max	
D50 um	0.6-1.0	
Al <sub>2</sub> O <sub>3</sub> %	0.01max	
Silicate %	0.01max	
Heavy metal %	0.008max	
Moisture %	0.2max	
105 °C Volatile 3hours %	0.3max	
Whiteness %	98min	
Residue on 240mesh	0.1%max	
PH	6.5-8.0	
Particle size distribution	<10um %	80min
	<5um %	60min
	<2um %	25min

### Applications:

Paint and coating

Ink

Rubber

Paper making

Plastic

Battery

**Packing:** 25kg/bag or follow customer's design.

**Storage:** Keep the product in dry and closed rooms at normal temperature and air humidity. To achieve best possible results, we recommend storage under the conditions stated above and use within 24 months from delivery.