

### Technical Data

Appearance	Fine Green Powder
Cr <sub>2</sub> O <sub>3</sub> Content	≥99%
Water Soluble Matter	≤0.20%
105 °C Volatile Matters	≤0.15%
Residues on Sieve 45μm	≤0.5%
Oil Absorption	15~25 g/100g
Cr <sup>6+</sup>	≤0.003%
Heat Resistance	600°C