

Properties		Specification
Viscosity in 5% toluene solution,mPa.s	CR2441	25-34
	CR2442	35-53
	CR2443	54-75
	CR2444	76-115
	CR244 high A	116-150
	CR244 high B	150 above
Viscosity in 15% toluene solution,mPa.s	CR2441	1000-2000
	CR2442	2001-3000
	CR2443	3001-5000
	CR2444	5001-7000
	CR244 high A	7001-9000
	CR244 high B	9001-10000
Peel strength,N/cm		90min.
Volatile matter,%		1.5max
Ash content,%		1.5max.